

ASD MICRO ABRASIVE RESISTANCE LAMINATE

TECHNICAL DATA SHEET



ASD MICRO ABRASIVE RESISTANCE LAMINATE ; less than 2 mm thick, according to EN 438-3, consisting of the surface layer on one side, having decorative colours are impregnated with feature of resistance to micro abrasive and a core made of layers of kraft paper impregnated with phenolic based resins. The back of the sheets is made suitable for adhesive bonding to substrates. They are available the types HGS, HGP, VGS, VGP.

PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT (max or min)	VALUES	
				HGS HGP	VGS VGP
HGP / HGS	Horizontal Grade Postforming Laminate / Horizontal Grade Standard Laminate		EXAMPLES OF TYPICAL APPLICATIONS Kitchen and office working surfaces, restaurant and hotel tables, doors and wall coverings in public areas, interior walls of public transport vehicles		
VGP / VGS	Vertical Grade Postforming Laminate / Vertical Grade Standard Laminate		EXAMPLES OF TYPICAL APPLICATIONS Front panels for kitchen, office and bathroom furniture, wall coverings, ceiling panels, shelves and furniture elements		
SURFACE QUALITY					
Surface Quality	EN 438-3	Spots, dirt and similar surface defects	mm ² /m ²	≤1	
		Fibres, hairs and scratches	mm/m ²	≤10	
DIMENSIONAL TOLERANCES					
Dimensional Tolerances	EN 438-2.5	Thickness tolerance (t: nominal thickness)	mm	0,5≤t<1,0mm:±0,10 mm 1,0<t<2.0 mm:±/-0,15 mm	
	EN 438-2.6	Lenght and width (b)	mm	+10/-0	
	EN 438-2.7	Straightness of edges (b)	mm/m	≤1,5	
	EN 438-2.8	Squareness	mm/m	≤1,5	
	EN 438-2.9	Flatness (a)	mm/m	60	
GENERAL PROPERTIES					
Resistance to surface wear	EN 438-2.10	Initial point	Revolutions	≥150	≥50
		Wear value	Revolutions	≥350	≥150
Resistance to immersion in boiling water	EN 438-2.12	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Resistance to water vapour	EN 438-2.14	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Resistance to dry heat (180 °C)	EN 438-2.16	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Resistance to weat heat (85 °C)	EN 12721	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Dimensional stability at elevated temperature	EN 438-2.17	Cumulative dimensional change	Longitudinal %	≤ 0,55	≤ 0,75
		Cumulative dimensional change	Transversal %	≤ 1,05	≤ 1,25
Resistance to impact with small diameter ball	EN 438-2.20	Spring Force	N	≥ 20	≥ 15
Resistance to impact with large diameter ball	EN 438-2.21	Drop height Indentation diameter	mm	≥ 800	≥ 600
			mm	≤ 10	≤ 10
Resistance to cracking under stress	EN 438-2.23	Appearance	Rating (min)	4	
Resistance to scratching	EN 438-2.25	Appearance	Rating (min)	3	2
Resistance to staining	EN 438-2.26	Appearance-Group 1&2	Rating (min)	5	
		Appearance-Group 3	Rating (min)	4	
Light fastness (Xenon-arc)	EN 438-2.27	Contrast	Grey scale rating	4 - 5	
Formability (HGP – VGP)	EN 438-2.31-32	Radius	L(parallel to fibre direction) mm	≤ 10 x laminate nominal thickness	
		Radius	T (right angles to fibre direction) mm	≤ 20 x laminate nominal thickness	
Resistance to blistering	EN 438-2.33-34	Time to blister	Seconds-nominal thickness<0,8mm	≥ 10	
		Time to blister	Seconds-nominal thickness≥0,8mm	≥ 15	
Density	EN ISO 1183	Density	g/cm ³	≥1,35	
OTHER PROPERTIES					
Mikro abrasive resistance	Martindale		Rating (min)	A1	

(a) : Provided that the laminates are stored in the manner and conditions recommended by the manufacturer the shall comply with the flatness requirements specified in Table 4 when measured in accordance with EN 438-2 Clause 9.

(b) :Tolerances for cut – to – size panels shall be agreed between supplier and purchaser.